

**PRODUCT INFORMATION SHEET**  
**3300 GS FLOORING SYSTEM**  
 1/4" TROWEL APPLIED MORTAR

**DESCRIPTION:**

3300 GS is a three-component flooring system, trowel applied at a minimum 1/4 inch. 3300 GS is U.S.D.A. acceptable for use in general service conditions and has excellent resistance to most acids, caustics, detergents and other corrosive materials. 3300 GS is designed to overlay entire floor surfaces, or repair smaller areas.

**ADVANTAGES:**

- Prepackaged - Easy To Use
- Excellent Adhesion
- Short Down Time – Quick Cure
- Easy To Clean - U.S.D.A. Acceptable
- Power trowelable
- Environmentally Safe

**USES:**

- Loading Docks
- Forklift Aisle ways
- General Service Floor Areas
- Industrial Production Facilities
- Warehouses

**SUPPLEMENTAL PRODUCTS:**

- 3500 Grout - Pitching and Filler
- 3000 VS  
Vertical Surfaces and Covets
- 1000 CS – Industrial Topcoat
- 3000 FLEX - Expansion Joint Filler
- Fibercoat Coating System  
Reinforced Wall Coating
- 3300 CR Veil Coat – Novolac Epoxy Topcoat

**PACKAGING AND COVERAGE:**

**3300 GS – Mortar** - packaged in batches -  
 1 Batch Kit – covers approximately 16 square feet at 1/4 inch (250mils), consisting of the following -  
 1 container – Part A (resin)  
 1 container – Part B (hardener)  
 1 bag – Part C (chemical resistant aggregate)

3 Batch Kit – Covers approximately 48 square feet at 1/4 inch (250 mils), consisting of the following -  
 1 container – Part A (resin)  
 1 container – Part B (hardener)  
 3 bags – Part C (chemical resistant aggregate)

Required: 3300 Primer

Required: 1000 CS Topcoat - One gallon covers approximately 100 square feet at 15 mils.

**PROPERTIES:**

<b>Compressive Strength</b>	11,500 psi ASTM C-579 (resin)
<b>Tensile Strength</b>	1,700 psi ASTM D-638 (resin)
<b>Flexural Strength</b>	3,500 psi ASTM C-580 (resin)
<b>Bond Strength</b>	Greater than 350 psi ASTM C-321 100% concrete failure
<b>Coefficient of Thermal Expansion</b>	1.2 x 10 <sup>-5</sup> in./in./°F
<b>Impact Strength</b>	130 in./lbs.
<b>Flammability</b>	Does not support combustion
<b>Water Absorption</b>	0.047% ASTM C-413
<b>Working Time at 75°F (24°C)</b>	20-30 minutes ASTM C-308
<b>Shelf Life</b>	1 Year
<b>Colors</b>	Grey, Red
<b>Solids by Content</b>	By Weight 100% By Volume 100%

**SURFACE PREPARATION:**

3300 GS may be installed only on clean, sound substrates

Concrete:

New concrete must be cured a minimum of 28 days. All coatings, oils, grease and unsound concrete must be removed. Concrete surfaces must then be acid etched, scarified or shot blasted to remove surface laitance. A good bonding tooth, the texture of 60 grit sandpaper, is desired for maximum adhesion, with removal of all surface glaze.

Metal Surfaces:

Blast the surface to near white SSPC-SP10-70 or NACE No. 2 using a Venturi blast nozzle with 100 psi air. The blasting media used shall be properly graded, clean, sharp, angular abrasive similar to Humble Abrasive Flint #7 (6-30) mesh, or Steel Grit (HG25).

**MIXING:**

Prior to starting, materials should be stored at 70°F (21°C) for at least 48 hours.

**Mortar** - Empty entire contents of Part B into Part A and stir thoroughly for 2 minutes. Slowly add the entire contents of Part C and mix for another 1-1/2 to 2 minutes.

As with all two-component systems, apply immediately after mixing, as exotherm will increase over time. The working time of the mortar will substantially be reduced if the material is left in a pail.

**APPLICATION:**

Substrate temperature should be 65°-85°F (18°-29°C) during installation and for 96 hours thereafter for complete cure. Do not apply 3300 GS when floor temperature is below 60°F (16°C). Pour the entire batch onto the floor as soon as blended and trowel smooth with a steel trowel.

Veil Coat: Pour system onto floor and pull tight across surface with a 12" squeegee. Back roll with a short nap roller to remove squeegee lines.

**CURE TIME:**

3300 GS will harden to foot traffic in 6-8 hours at 75°F (24°C). Maximum chemical resistance will occur after 96 hours of cure time at 75°F (24°C).

**CLEANUP:**

Cured or hardened 3300 GS will bond to practically all surfaces and is extremely difficult to remove. Clean all tools and mixer immediately after use with acetone or other solvent based cleaners.

**SAFETY:**

Avoid skin contact. If eye contact occurs, flush with water and consult a physician immediately. Keep work areas well ventilated. Never seal a container of mixed Part A and B as the continuing exothermic reaction may cause container to explode. 3300 GS Material Safety Data Sheets are available upon request.

**NOTE:**

Refer to 3300 GS Instruction for use.

**IMPORTANT NOTICE TO PURCHASER:**

The following is made in lieu of all warranties, expressed or implied. Seller and manufacturer's only obligation shall be to replace such quantities of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss or damage, direct or consequential arising out of the use of or inability to use the product. Before using, user shall determine the suitability of the product for his intended use, and user assumes all risks and liability whatsoever in connection therewith. The foregoing may not be altered unless written authorization is received from PROTECTIVE FLOORINGS AND LININGS, A DIVISION OF A. W. CHESTERTON.